

TEST REPORT: 7191025103-CHM12-01-LSM-CR2

Date: 03 FEB 2012

Tel: +65 68851335 Fax: +65 67784301

Client's Ref: QM-0112-056

Email: Sihai.LI@tuv-sud-psb.sg

Note: This report is issued subject to the Testing and Certification Regulations of the TÜV SÜD Group and the General Terms and Conditions of Business of TÜV SÜD PSB Pte Ltd. In addition, this report is governed by the terms set out within this report.



PSB Singapore

Choose certainty.
Add value.

SUBJECT

Chemical Resistance Testing of "MAICA Compact Laminates"

CLIENT

Maica Laminates Sdn Bhd
5100, Lorong Mak Mandin 5,
Mak Mandin Industrial Estate,
13400 Butterworth
Penang, Malaysia

Attn: Mr. Kow Cheng Fung

SAMPLE SUBMISSION / TEST DATE

31 Oct & 22 Dec 2011 / 11 Nov 2011 - 13 Jan 2012

SAMPLE DESCRIPTION

3 sets of "MAICA Compact Laminates" were received

Sample Reference

Colour : Black
Code : Nacht
Size : 16 mm (H) x 100 mm (W) x 100 mm (L)
Qty : 106

Colour : White
Code : Schnee
Size : 16 mm (H) x 100 mm (W) x 100 mm (L)
Qty : 111

Colour : Grey
Code : Asche
Size : 16 mm (H) x 100 mm (W) x 100 mm (L)
Qty : 107



Laboratory:
TÜV SÜD PSB Pte. Ltd.
Testing Services
No.1 Science Park Drive
Singapore 118221

Phone : +65-6885 1333
Fax : +65-6776 8670
E-mail: testing@tuv-sud-psb.sg
www.tuv-sud-psb.sg
Co. Reg : 199002667R

Regional Head Office:
TÜV SÜD Asia Pacific Pte. Ltd.
3 Science Park Drive, #04-01/05
The Franklin, Singapore 118223
TÜV[®]



METHOD OF TEST

BS EN 438-2:2005

High-pressure decorative laminates (HPL). Sheets based on thermosetting resins (usually called laminates).

Determination of properties

Clause 26: Resistance to Staining

The above chemical test was conducted in accordance with BS EN 438-2:2005. Small quantity of test chemical is applied on the surface of the laminates and is covered to restrict evaporation.

The test parameters are described as follows:

Temperature : 23 ± 2 °C

Duration : 24 hours

After the test, the surface is washed with distilled water and dried with a clean cloth before visual inspection and evaluation.

The evaluation of the effect on the surface is expressed in accordance with the following rating scale

Rating	Description
5	No Visible Change
4	Slight Change of gloss and / or colour only visible at certain viewing angles
3	Moderate marked change of gloss and / or colour
2	Marked change of gloss and / or colour
1	Surface distortion and / or blistering

TEST REPORT: 7191025103-CHM12-01-LSM-CR2
03 FEB 2012



PSB Singapore

RESULTS

No.	Group	%	Rating		
			Nacht Black	Schnee White	Asche Grey
Acid					
1	Acetic Acid	100	5	5	5
2	Dichromate Acid	5	5	5	5
3	Chromic Acid	60	5	5	5
4	Formic Acid	90	5	5	5
5	Hydrochloric Acid	10	5	5	5
6	Hydrochloric Acid	37	5	5	5
7	Hydrofluoric Acid	48	4	4	2
8	Nitric Acid	20	5	5	5
9	Nitric Acid	30	5	5	5
10	Nitric Acid	65	4	4	4
11	Nitric Acid	70	4	4	4
12	Nitric Acid 65% : Hydrochloric Acid 37%	1:3	4	3	3
13	Perchloric Acid	60	5	5	5
14	Phosphoric Acid	85	5	5	5
15	Sulphuric Acid	25	5	5	5
16	Sulphuric Acid	33	5	5	5
17	Sulphuric Acid	77	5	5	5
18	Sulphuric Acid	85	5	5	5
19	Sulphuric Acid	98	4	4	4
20	Sulphuric Acid 77% :Nitric Acid 70%	1:1	4	4	4
21	Sulphuric Acid 85%:Nitric Acid 70%	1:1	4	4	4
Bases					
22	Ammonium Hydroxide	28	5	5	5
23	Sodium Hydroxide	10	5	5	5
24	Sodium Hydroxide	20	5	5	5
25	Sodium Hydroxide	40	5	5	5
26	Sodium Hydroxide Flake	-	5	5	5

RESULTS (cont'd)

No.	Group	%	Rating		
			Nacht Black	Schnee White	Asche Grey
Biologic stains					
27	Acridine Orange	1	5	4	5
28	Alizarin Complexone Dihydrate	1	5	5	5
29	Aniline Blue (Water Soluble)	1	5	5	5
30	Basic Fuchsin	1	4	4	4
31	Carbol Fuchsin	1	3	3	3
32	Carmine	1	5	5	5
33	Eosin B	1	5	5	5
34	Gentian Violet (Dye)	1	5	5	5
35	Giemsa Stain	1	5	5	5
36	Kongo Red	1	5	4	5
37	Malachite Green Oxalate	1	5	5	5
38	Methyl Violet 2B	1	5	5	5
39	Methylene Blue	1	5	5	5
40	Safranin O	1	5	5	5
41	Sudan III	1	5	5	5
42	Wright Stain	1	5	5	5
Halogens					
43	Iodine 0.1N	-	5	3	3
44	Iodine Crystal	-	4	2	2
45	Tincture of Iodine	-	4	2	2
Salts					
46	Copper Sulphate	10	5	5	5
47	Potassium Iodite	10	5	5	5
48	Potassium Permanganate	10	2	2	2
49	Silver Nitrate	1	5	5	5
50	Sodium Hypochloride	13	5	5	5
51	Sodium Sulfide	saturated	5	5	5
52	Zinc Chloride	saturated	5	5	5
Organic Chemicals					
53	Amyl Acetate	-	5	5	5
54	Benzene	-	5	5	5
55	Cresol	-	5	5	5
56	Dimethylformamide	-	5	5	5
57	Formaldehyde	37	5	5	5
58	Furfural	-	4	3	3

RESULTS (cont'd)

No.	Group	%	Rating		
			Nacht Black	Schnee White	Asche Grey
Organic Chemicals					
59	Gasoline	-	5	5	5
60	Methyl Ethyl Ketone	-	5	5	5
61	n-Butyl Acetate	-	5	5	5
62	Phenol	90	5	5	5
63	Xylene	-	5	5	5
Solvents					
64	Acetic Anhydride	-	5	5	5
65	Acetone	-	5	5	5
66	Acetonitrile	-	5	5	5
67	Butyl Alcohol	-	5	5	5
68	Carban Tetrachloride	-	5	5	5
69	Chloroform	-	5	5	5
70	Dichloro Acetic Acid	-	5	5	5
71	Dichloromethane	-	5	5	5
72	Diethyl Ether	-	5	5	5
73	Dioxane	-	5	5	5
74	Ethyl Alcohol	-	5	5	5
75	Ethyl Acetate	-	5	5	5
76	Ethylene Glycol	-	5	5	5
77	n-Hexane	-	5	5	5
78	Methyl Alcohol	-	5	5	5
79	Methylene Chloride	-	5	5	5
80	Methylisobutylketone	-	5	5	5
81	Mono Chlorobenzene	-	5	5	5
82	Naphthalene	-	5	5	5
83	Tetrahydrofuran	-	5	5	5
84	Toluene	-	5	5	5
85	Trichloroethylene	-	5	5	5



RESULTS (cont'd)

No.	Chemical	%	Rating		
			Nacht Black	Schnee White	Asche Grey
Acid					
86	Acetic Acid	98	5	5	5
87	Sulphuric Acid	96	4	4	4
Salts					
88	Silver Nitrate	saturated	5	3	5
89	Iron (III) Chloride	10	5	5	5
90	Sodium Chloride	10	5	5	5
Organic Chemicals					
91	Hydrogen Peroxide	30	5	5	5

LEOW SIONG MING
TECHNICAL EXECUTIVE

for DR LI SIHAI
AVP / SENIOR CHEMIST
COATINGS & INDUSTRIAL CHEMICALS
CHEMICAL & MATERIALS

TEST REPORT: 7191025103-CHM12-01-LSM-CR2
03 FEB 2012



PSB Singapore

Please note that this Report is issued under the following terms :

1. This report applies to the sample of the specific product/equipment given at the time of its testing/calibration. The results are not used to indicate or imply that they are applicable to other similar items. In addition, such results must not be used to indicate or imply that TÜV SÜD PSB approves, recommends or endorses the manufacturer, supplier or user of such product/equipment, or that TÜV SÜD PSB in any way "guarantees" the later performance of the product/equipment. Unless otherwise stated in this report, no tests were conducted to determine long term effects of using the specific product/equipment.
2. The sample/s mentioned in this report is/are submitted/supplied/manufactured by the Client. TÜV SÜD PSB therefore assumes no responsibility for the accuracy of information on the brand name, model number, origin of manufacture, consignment or any information supplied.
3. Nothing in this report shall be interpreted to mean that TÜV SÜD PSB has verified or ascertained any endorsement or marks from any other testing authority or bodies that may be found on that sample.
4. This report shall not be reproduced wholly or in parts and no reference shall be made by the Client to TÜV SÜD PSB or to the report or results furnished by TÜV SÜD PSB in any advertisements or sales promotion.
5. Unless otherwise stated, the tests were carried out in TÜV SÜD PSB Pte Ltd, No.1 Science Park Drive Singapore 118221.

July 2011

